

GenieMat® RSTo3

ROLL-OUT SOUND CONTROL UNDERLAYMENT



PRODUCT SPECIFICATIONS

PRODUCT NAME:	GenieMat RSTo3
DESCRIPTION:	GenieMat RST is a flat, resilient underlayment made from up to 94% recycled rubber, designed for installation directly under various hard-surface floor finishes, including tile, vinyl plank, and wood flooring.
APPLICATION:	Used in concrete and wood-frame construction to provide superior sound control, especially in multifamily housing, high-rises, and commercial buildings. It is engineered to protect ceramic tile, porcelain, and stone from substrate cracks.
FEATURES AND BENEFITS:	• Significantly reduces impact sound • Mold, bacteria, fungi, and water resistant • Exceeds pass criteria for point load test for crack isolation membrane (ANSI 118.12) • Can be installed directly under hard surface or resilient floor coverings • Meets requirements for VOC emissions (IAQ test, ASTM D5116/ISO 16000-9) • Complete floor covering system warranty available • Floorscore® certified • Third-party verified EPDs available • Qualifies for LEED® points
DIMENSION:	Roll: 4' wide, 50' long (nom. 1.22 m wide, nom. 15.24 m long)
THICKNESS:	1/8" (nom. 3 mm)
WEIGHT:	120 lb/Roll (54.4 kg/Roll)
AREA:	200 ft² (18.58 m²)
DENSITY:	Shall be > 62 lb/ft³ (1000 kg/m³)
QUANTITY/PALLET:	16

GenieMat® RSTo3

ROLL-OUT SOUND CONTROL UNDERLAYMENT



TECHNICAL DATA

TYPE A HARDNESS (ASTM D2240):	50 (±5) Durometer
REDUCTION OF IMPACT SOUND PRESSURE LEVEL (ASTM E492/E2179, ISO 10140-3):	GenieMat RSTo3 tested over 8" (nom. 200 mm) concrete slab with wood laminate floor covering, no ceiling, IIC 56 ($L_{n,w}$ 54) and Δ IIC 23dB (ΔL_w 19dB)
NATURAL FREQUENCY:	Shall not be greater than 92 Hz at 400 psf (0.02 MPa) load
HIIC (ASTM E3222):	Shall be ≥ 58 when tested on an 8" (nom. 200 mm) concrete slab with vinyl Shall be ≥ 55 when tested on an 8" (nom. 200 mm) concrete slab with engineered wood Shall be ≥ 45 when tested on a 6" (nom. 150 mm) concrete slab with tile
POINT LOAD TEST FOR CRACK ISOLATION MEMBRANES (ANSI 118.12):	Exceeds pass criteria
PUNCTURE TESTING WHEN INSTALLED UNDER LUXURY VINYL TILE (ASTM F924):	No change when compared to puncture failure limit of luxury vinyl tile tested without underlayment
ROBINSON WHEEL TILE TEST (ASTM C627):	Extra heavy commercial with tile
RESISTANCE TO IMPACT WHEN INSTALLED UNDER LUXURY VINYL TILE (ASTM F1265):	Luxury vinyl tile shows no signs of breaking or cracking and meets standard criteria
ROLLING LOAD INDENTATION WHEN INSTALLED UNDER LUXURY VINYL TILE (ASTM F2753):	Luxury vinyl tile shows no signs of indentation and plank separation for 12,500 cycles
DYNAMIC STIFFNESS (ASTM D5992, ISO 4664-1):	6922 lbf/in ³ (1879 MN/m ³)
STATIC STIFFNESS (ASTM D5992, ISO 4664-1):	979 lbf/in ³ (266 MN/m ³)
DYNAMIC-STATIC STIFFNESS RATIO (ASTM D5992, ISO 4664-1):	7.07

GenieMat® RSTo3

ROLL-OUT SOUND CONTROL UNDERLAYMENT



VOC EMISSIONS (CDPH/EHLB
STANDARD METHOD v1.2-2017):

FloorScore® certified

LOAD/DEFLECTION FOR TILE
FLOORS:

Shall not have deflection greater than 2% of the thickness at loads up to 1,000 psf (nom. 48 kPa)

THERMAL RESISTANCE (R-VALUE):

0.128 ft²·°F·hr/BTU (0.023 m²·K/W)

THERMAL TRANSMITTANCE
(U-VALUE):

7.808 BTU/ hr·°F·ft² (44.333 W/m²·K)

WARRANTY:

Shall have a 25 year warranty as an approved component of a full waterproofing floor system

TEMPERATURE STABILITY:

-40°F to +240°F (-40°C to +115°C)



AROUND THE WORLD.

PLITEQ INC.

131 Royal Group Crescent
Vaughan, ON
L4H 1X9 Canada

4211, Yonge Street,
Suite 404, Toronto, ON
M2P 2A9 Canada

2015 Main St,
Vancouver, BC
V5T 3C2 Canada

T.+1 416 449 0049
info@pliteq.com
www.pliteq.com

PLITEQ (DE)

251 Little Falls Drive
Wilmington, DE
19808
United States of America

PLITEQ (AZ)

11701 N. 132nd Drive
Surprise, AZ
85379
United States of America

T.+1 480 805 5560
info@pliteq.com
www.pliteq.com

PLITEQ (UK) LTD.

Office 205, Orega High
Holborn, 16 High Holborn,
London, WC1V 6BX
United Kingdom

T.+44 203 9846444
info@pliteq.co.uk
www.pliteq.co.uk

PLITEQ MEXICO

Calz. Gral. Mariano
Escobedo 476-piso 12
Chapultepec Morales,
Anzures,
Miguel Hidalgo, 11590
Ciudad de México, CDMX
Mexico

T.+52 1 938 164 1551

PLITEQ ASIA PACIFIC PTE LTD.

#19-13, 101 Cecil Street,
Tong Eng Building, 069533
Singapore

T.+65 6813 2017
info@pliteq.sg
www.pliteq.sg

PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre
Dubai Investment Park
PO Box 473 512
United Arab Emirates

T. +971 4 567 4944
info@pliteq.ae
www.pliteq.ae

PLITEQ AUSTRALIA PTY LTD.

68-82 York St, South
Melbourne, VIC, 3205
Australia
ABN: 86 675 027 433

T.+61 455 203 269
info@pliteq.com.au
www.pliteq.com.au

