

GENIEBOARD® 302

HIGH DENSITY GYPSUM FIBREBOARD



Product Specification


Product Name:	GenieBoard® 302
Description:	A universal dry flooring board that can be used as an alternative to poured screed, or multiple plywood and cement board layers. Connects with a 50mm shiplap joint, which is glued and fixed with 22mm screws or staples at 200mm centres along board joints.
Application:	Can be used directly under all flooring types and on top of all GenieMat® products in lightweight and heavyweight buildings.
Dimensions:	500 mm x 1500 mm (Overlap 50mm)
Coverage:	0.75 m ²
Thickness:	nom. 25mm
Board Weight:	29 kg/m ²





Technical Data

Acoustic Performance: (ISO 10140-2:210 & ISO 10140-3:2010)	Shall be $R_w (+C_{tr})$ 65 (-10)dB, $L_{n,w}$ 50dB, and $\Delta L_{n,w}$ 29 dB when tested on bare 140mm concrete slab , no ceiling. +5dB for airborne sound, 12dB improvement on Part E impact Sound
Fire Rating: (EN 13501-1:2018)	A2fl-s1
Thermal Resistance:	0.07 (m ² *K)/W
Thermal Conductivity:	0.30 W/(m*K)
Water vapour permeability: (EN 12086)	13μ when 0/50 (A, dry) under condition 23 12μ when 50/93 (C, wet) under condition 23
Maximum Point Load:	3kN A load area of at least 7850 mm ² . (Stamp Ø = 100 mm).

GENIEBOARD® 302

HIGH DENSITY GYPSUM FIBREBOARD



-  Floor Finish
-  GenieBoard 302
-  GenieMat FF10
-  Mass Timber Structure



AROUND THE WORLD.

PLITEQ INC.

131 Royal Group Crescent
Vaughan, ON
L4H 1X9 Canada

4211, Yonge Street,
Suite 404, Toronto, ON M2P
2A9 Canada

2015 Main St,
Vancouver, BC
V5T 3C2 Canada

T.+1 416 449 0049
info@pliteq.com
www.pliteq.com

PLITEQ (DE)

251 Little Falls Drive
Wilmington, DE
19808
United States of America

PLITEQ (AZ)

11701 N. 132nd Drive
Surprise, AZ
85379
United States of America

T.+1 480 805 5560
info@pliteq.com
www.pliteq.com

PLITEQ MEXICO

Calz. Gral. Mariano Escobedo
476-piso 12 Chapultepec
Morales, Anzures,
Miguel Hidalgo, 11590
Ciudad de México, CDMX
Mexico

T.+52 1 938 164 1551

PLITEQ (UK) LTD.

Office 205, Orega High
Holborn, 16 High Holborn,
London, WC1V 6BX
United Kingdom

T.+44 203 9846444
info@pliteq.co.uk
www.pliteq.co.uk

PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre
Dubai Investment Park
PO Box 473 512
United Arab Emirates

T. +971 4 567 4944
info@pliteq.ae
www.pliteq.ae

PLITEQ ASIA PACIFIC PTE LTD.

#19-13, 101 Cecil Street,
Tong Eng Building, 069533
Singapore

T.+65 6813 2017
info@pliteq.sg
www.pliteq.sg

PLITEQ AUSTRALIA PTY LTD.

72 York Street, South
Melbourne, VIC, 3205
Australia

T.+61 3 9018 7696
info@pliteq.com.au
www.pliteq.com.au



© Pliteq Inc. 2025.

®™ Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.