

GENIEMAT[®] FAS4

FLOORING ADHESIVE SYSTEM



PRODUCT SPECIFICATION

PRODUCT NAME: GenieMat FAS4

DESCRIPTION: GenieMat FAS4 wet set / semi wet set adhesive. It is solvent-free, non-flammable, has low-odour, demonstrates water resistant benefits of a hard-set adhesive, features long working time, is very quick to use and easy to trowel. This specially formulated adhesive has plasticiser migration resistance that allows installation of a broad variety of vinyl floor products.

APPLICATION: GenieMat FAS4 is used for bonding GenieMat sound control underlayments to various subfloors/substrates, and for bonding all specified finish floors and coverings, including vinyl floor products, to GenieMat sound control underlayments.

APPEARANCE: Smooth, medium viscosity, easy to trowel, cream.

INSTALLATION METHOD: For non porous surface allow the adhesive to tack off.
Wet set application for porous surfaces: allow flash time of 5-20 minutes depending on temperature and humidity.

WORKING TIME: 10 - 30 minutes, depending on temperature and humidity

SHELF LIFE: 1 year in unopened container at 21°C

GENIEMAT[®] FAS4

FLOORING ADHESIVE SYSTEM



PRODUCT SPECIFICATION CONTINUED

TROWEL SELECTION AND COVERAGE:

Coverage is approximate and may vary depending on porosity of substrate and angle at which the trowel is held. It is the installer's responsibility to apply the proper amount of adhesive for the job condition.

Installation:	Trowel Size* & Notch:	Coverage:
GenieMat to porous substrate:	A2 Notch Trowel	41 - 47 m ²
GenieMat to non-porous substrate:	A1 / A2 Notch Trowel	41 - 54 m ²
Vinyl tile and plank to GenieMat :	A2 Notch Trowel for structured backings	41 - 47 m ²
	A1 Notch Trowel for smooth backings	47 - 54 m ²
Solid vinyl sheet to	A1 / A5 Notch Trowel	47 - 61 m ²

QUANTITY: Bucket: 14 kg

TECHNICAL DATA

SUBSTRATE RELATIVE HUMIDITY TEST (BS8203): 75 % RH

APPLICATION TEMPERATURE: Best applied between 18 - 25 °C, with the floor temperature above 15 °C

APPLICATION RELATIVE HUMIDITY: Best applied relative air humidity below 65 %

FREEZE/THAW STABILITY: Stable to -14 °C



AROUND THE WORLD.

CONTACT US

PLITEQ NORTH AMERICA

131 Royal Group Crescent
Vaughan, ON
L4H 1X9 Canada

T. + 1 416 449 0049

info@pliteq.com
www.pliteq.com

PLITEQ UK

Irongate House
22-30 Dukes Place
London
EC3A 7LP

T. + 44 203 9846444

info@pliteq.co.uk
www.pliteq.co.uk

PLITEQ MIDDLE EAST

European Business Centre
Dubai Investment Park
PO Box 473 512
Dubai, UAE

T: +971 4 567 4944

info@pliteq.ae
www.pliteq.ae

PLITEQ ASIA PACIFIC

101 Cecil Street #19-13
Tong Eng Building Singapore
069533

T. +65 8452 6865

info@pliteq.sg
www.pliteq.sg



© Pliteq Inc.

®™ Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.