

# GENIEMAT<sup>®</sup> FF03NP-S

## Sound Control Underlayment



### Product Specification

Product Name: **GenieMat FF03NP-S**

Material: Robust reduced sound transmission mat made from 94% recycled material.

Description: Designed to reduce the transmission of impact sound generated by footfall noise for various types of structures for both residential and commercial use. Can be used directly under screed or gypsum concrete in concrete, steel and wood construction.

- Features and Benefits:
- Tested by 3rd party accredited laboratories to significantly reduce impact sound
  - Mould, bacteria, fungi, and water resistant
  - Qualifies for LEED<sup>®</sup> points
  - Easy to install
  - Will not fail under high point loads
  - CE Marked

Dimension: Sheets: 1.22 m wide, 2.13 m long

Coverage: 2.6 m<sup>2</sup>

Thickness: nom. 3 mm (2.5mm +/- 0.5mm) (tolerances are pursuant to ISO 3302-1)

Roll Weight: 4.75 kg/sheet

Sheets/pallet: 190



# GENIEMAT<sup>®</sup> FF03NP-S

## Sound Control Underlayment



### Technical Data

Building code: Meets and improves on Approved Document E impact performance requirement, providing  $\Delta L_{nw}$  24 under 60mm screed


Tensile Strength & Elongation at Break (ASTM D412)  $\geq 0.48$  MPa  
 $\geq 45\%$


Type A Hardness (ASTM D2240): 45 durometer

Temperature Stability:  $-40^{\circ}\text{C}$  to  $+115^{\circ}\text{C}$  ( $-40^{\circ}\text{F}$  to  $+240^{\circ}\text{F}$ )

Thermal resistance (R-value):  $0.06$  (m<sup>2</sup>K)/W

Thermal transmittance (U-value):  $16.67$  W/(m<sup>2</sup>K)





## AROUND THE WORLD.

### PLITEQ INC.

131 Royal Group Crescent  
Vaughan, ON  
L4H 1X9 Canada

4211, Yonge Street,  
Suite 404, Toronto, ON  
M2P 2A9 Canada

2015 Main St,  
Vancouver, BC  
V5T 3C2 Canada

T.+1 416 449 0049  
info@pliteq.com  
www.pliteq.com

### PLITEQ (DE)

251 Little Falls Drive  
Wilmington, DE  
19808  
United States of America

### PLITEQ (AZ)

11701 N. 132nd Drive  
Surprise, AZ  
85379  
United States of America

T.+1 480 805 5560  
info@pliteq.com  
www.pliteq.com

### PLITEQ (UK) LTD.

Office 205, Orega High  
Holborn, 16 High Holborn,  
London, WC1V 6BX  
United Kingdom

T.+44 203 9846444  
info@pliteq.co.uk  
www.pliteq.co.uk

### PLITEQ MEXICO

Calz. Gral. Mariano  
Escobedo 476-piso 12  
Chapultepec Morales,  
Anzures,  
Miguel Hidalgo, 11590  
Ciudad de México, CDMX  
Mexico

T.+52 1 938 164 1551

### PLITEQ ASIA PACIFIC PTE LTD.

#19-13, 101 Cecil Street,  
Tong Eng Building, 069533  
Singapore

T.+65 6813 2017  
info@pliteq.sg  
www.pliteq.sg

### PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre  
Dubai Investment Park  
PO Box 473 512  
United Arab Emirates

T. +971 4 567 4944  
info@pliteq.ae  
www.pliteq.ae

### PLITEQ AUSTRALIA PTY LTD.

68-82 York St, South  
Melbourne, VIC, 3205  
Australia  
ABN: 86 675 027 433

T.+61 455 203 269  
info@pliteq.com.au  
www.pliteq.com.au

