GENIEMAT® FF25 ROLL-OUT FLOATING FLOORS



PATENTS: US 8,240,430 US 8,556,029 CA 2,500,956 CA 2,503,420

PRODUCT SPECIFICATION

Product Name:	GenieMat FF25
DESCRIPTION:	Robust dimpled rubber pad made up to 94% recycled rubber content used when superior sound control is required in mechanical rooms, sound studios, home theatres, entertainment venues, medical facilities, exercise, gym, and dance floors, and commercial, industrial, and multifamily housing.
Application:	Shock absorbing and impact sound reducing pad to be used under screed, light-weight and full-weight concrete, cement board, and GenieBoard .
FEATURES AND BENEFITS:	 Significantly increases L_{n,w} and R_w ratings Qualifies for LEED® points No potential mould-producing fibreglass Easy to install, rolls out quickly, stays in place, and doesn't need to be adhered or fastened to substrate
DIMENSION:	Rollgood: 1.22 m wide, 4.57 m long
THICKNESS:	nom. 25 mm max. nom. 14 mm min.
ROLL WEIGHT:	57.2 kg/roll
Roll Area:	$5.57\mathrm{m}^2$

GENIEMAT® FF25 **ROLL-OUT FLOATING FLOORS**



PATENTS: US 8,240,430 US 8,556,029 CA 2,500,956 CA 2,503,420

TECHNICAL DATA

GenieMat FF25 tested over 175 mm 5-ply cross laminated timber (CLT) with 100 mm concrete topping, no ceiling, L_{n,w} 60 dB **GenieMat FF25** tested over 140 mm concrete slab with 100 mm concrete

LABORATORY IMPACT **INSULATION CLASS** (BS EN ISO 10140-3): topping, no ceiling, $L_{n,w}$ 45 and $\Delta L_{n,w}$ 32 dB as per BS EN ISO 10140-8

GenieMat FF25 tested over 140 mm concrete slab with 60 mm screed, no ceiling, $L_{n,w}$ 47 and $\Delta L_{n,w}$ 30 dB as per BS EN ISO 10140-8

GenieMat FF25 tested over TJI joist with vinyl, GenieMat RST02, 40 mm screed, and OSB, ceiling consist of GenieClip RST and 2 layers of plasterboard, L_{n,w} 46 dB

DEFLECTION CREEP:

Shall not experience deformation greater than 3% of the total thickness

under a load of 700 N for a constant 24 hour period

NATURAL FREQUENCY:

18 Hz at 0.01 MPa load 16 Hz at 0.02 MPa load 15 Hz at 0.1 MPa load

VOC EMISSIONS:

(CDPH/EHLB STANDARD METHOD v1.2-2017)


FloorScore certified

BUTADIENE PURITY AND HYDROCARBON IMPURITIES: (ASTM D2593)

None detected

TEMPERATURE STABILITY:

-40°C to +80°C





AROUND THE WORLD.

CONTACT US

PLITEQ NORTH AMERICA

131 Royal Group Crescent Vaughan, ON L4H 1X9 Canada

T. + 1 416 449 0049

info@pliteq.com www.pliteq.com

PLITEQ UK

Irongate House 22-30 Dukes Place London EC3A 7LP

T. + 44 203 9846444

info@pliteq.co.uk www.pliteq.co.uk

PLITEQ MIDDLE EAST

European Business Centre Dubai Investment Park PO Box 473 512 Dubai, UAE

T: +971 4 567 4944

info@pliteq.ae www.pliteq.ae

PLITEQ ASIA PACIFIC

101 Cecil Street #19-13 Tong Eng Building Singapore 069533

T. +65 8452 6865

info@pliteq.sg www.pliteq.sg































© Pliteq Inc.

*** Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.