

# GENIEMAT<sup>®</sup> RST02

## Sound Control Underlayment



### Product Specification

Product Name:	<b>GenieMat RST02</b>
Dimension:	Rollgood: 1.22 m wide, 22.9 m long (4' wide, 75' long)
Coverage:	27.94 m <sup>2</sup>
Thickness:	nom. 2 mm (5/64")
Density:	Shall be > 1000 kg/m <sup>3</sup>
Roll Weight:	54 .4 kg

### Technical Data

Reduction of Impact Sound Pressure Level: (ISO 10140)	$\Delta L_{n,w}$ performance of 20 dB under LVT $\Delta L_{n,w}$ performance of 16 dB under ceramic tile
Natural Frequency	Shall not be greater than 92 Hz @ 19.2 kN/m <sup>2</sup> (400 psf) loading
Building code	Meets and improves on Approved Document E impact performance requirements by 9 dB when used under LVT or hardwood flooring. Meets and exceeds on BCA part F5 impact performance requirements
Point Load Test for Crack Isolation Membranes: (ANSI 118.12)	Exceeds pass criteria
Puncture Testing When Installed Under Luxury Vinyl Tile: (ASTM F924)	No change when compared to puncture failure limit of luxury vinyl tile tested without underlayment
Resistance to Impact When Installed Under Luxury Vinyl Tile: (ASTM F1265)	Luxury vinyl tile shows no signs of breaking or cracking and meets standard criteria
Rolling Load Indentation When Installed Under Luxury Vinyl Tile: (ASTM F2753)	Luxury vinyl tile shows no signs of indentation and plank separation for 12,500 cycles



# GENIEMAT<sup>®</sup> RST02

## Sound Control Underlayment



### Technical Data

Temperature Stability: -40°C to +115°C (-40°F to +240°F)

Thermal resistance (R-value): 0.015 (m<sup>2</sup>K)/W

Thermal transmittance (U-value): 66.5 W/(m<sup>2</sup>K)

Robinson Wheel Test with tile (ASTM C627): Extra Heavy Commercial





# AROUND THE WORLD.



## PLITEQ INC.

131 Royal Group Crescent  
Vaughan, ON  
L4H 1X9 Canada

T. + 1 416 449 0049

info@pliteq.com  
www.pliteq.com

## PLITEQ (UK) LTD.

Irongate House  
22-30 Dukes Place  
London  
EC3A 7LP

T. + 44 203 9846444

info@pliteq.co.uk  
www.pliteq.co.uk

## PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre  
Dubai Investment Park  
PO Box 473 512  
Dubai, UAE

T: +971 4 567 4944

info@pliteq.ae  
www.pliteq.ae

## PLITEQ ASIA PACIFIC PTE LTD.

101 Cecil Street #19-13  
Tong Eng Building Singapore  
069533

T. +65 8452 6865

info@pliteq.sg  
www.pliteq.sg



© Pliteq Inc.

®™ Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.